

☐ In my patents list | Print

FIBER FOR REINFORCING CEMENT

Bibliographic data

[Original document](#)

[INPADOC legal status](#)

Publication number: JP7010621 (A)

Publication date: 1995-01-13

Inventor(s): TAKAI YOSUKE; KURIKAWA HARUYUKI; YAMASHITA KENJI

Applicant(s): DAIWA SPINNING CO LTD

Classification:

- international: C04B16/06; C04B20/10; D06M11/00; D06M11/28; D06M101/00; D06M101/16; D06M101/18; D06M101/20; D06M101/22; D06M101/26; C04B16/00; C04B20/00; D06M11/00; (IPC1-7): C04B16/06; C04B20/10; D06M11/28

- European: C04B20/10F6

Application number: JP19930176068 19930622

Priority number(s): JP19930176068 19930622

[View INPADOC patent family](#)

[View list of citing documents](#)

[Report a data error here](#)

Abstract of JP 7010621 (A)

PURPOSE: To improve affinity of a fiber for cement by treating the fiber so as to readily bond cement particles to fiber surface in mixing the fiber with cement. **CONSTITUTION:** 2-200wt. % (based on fiber weight) of iron(III)chloride component is bonded to the surface of fiber by immersing a fiber into an aqueous solution of iron(III) chloride to provide a fiber for reinforcing cement, capable of developing tackiness on the fiber surface by converting this iron(III)chloride component into gel-like iron hydroxide in mixing the fiber with cement. When the fiber is mixed into cement slurry, cement particles are bonded to the surface of fiber to improve affinity for cement and the fiber is favorably dispersed in the cement slurry by stirring to enhance flexural strength of cement formed article.

Data supplied from the esp@cenet database — Worldwide